



TECHNICAL INFORMATION

MULTI-PURPOSE PRIMER

DESCRIPTION

Multi-purpose primer made from modified epoxy ester resins, containing zinc phosphate as an anti-corrosive pigment. It facilitates adherence of subsequent layers on galvanized metals, aluminium, zinc, etc.

Characteristics:

- Excellent adherence to metal surfaces.
- Resistant to water, corrosion and the elements.
- Excellent smoothing and easily brushed.
- Great hardness and resistant to scratches.
- A single component.
- Fast drying.

TECHNICAL DATA

Fixed vehicle: Modified epoxy ester resin.

Colour: White, Rust Red, Grey, Black and Green.

Finish: Semi-matt.

Solids by weight: 72.5 %

Solids by volume: 55.0 %

Viscosity: 95 – 105 KU (at 23 ± 2 °C)

Specific weight: 1.30 – 1.40 Kg./l (at 23 ± 2 °C)

Theoretical coverage: 8 – 12 m²/l and coat, according to surface.

Drying time: 30 – 60 minutes.

Re-Coat: 6 – 8 hours.

Solvent: Aliphatic hydrocarbons.

APPLICATION

Anti-corrosion primer for ferrous and non-ferrous surfaces, both indoors as well as outdoors, which facilitates the adherence of subsequent layers on galvanized metals, aluminium, zinc, etc.

INSTRUCTIONS FOR USE

Methods of application: Brush, roller or gun.

Thinners and cleaning of tools: SYNTHETIC AND OIL SOLVENT

The surfaces to be painted must be dry and free of dust, rust, oil, etc.



TECHNICAL INFORMATION

MULTI-PURPOSE PRIMER

- Non-painted surfaces:
 - Ferrous or non-ferrous: The surface to be painted should be dry and free of dust, rust, oil, etc. Apply two layers of MULTI-PURPOSE PRIMER.
- Painted surfaces:
 - If the paintwork is in poor condition, it should be totally removed and then the procedure is as for non-painted surfaces.
 - If the paintwork is in good condition, sand down and apply MULTI-PURPOSE PRIMER.

If you wish to colour it, you can use DECOLOR UNIVERSAL DYE, at most 5%.

General recommendations:

- Apply at temperatures between 5 °C and 35 °C.
- Do not apply in strong sunlight or where the surfaces are hot.
- Homogenize the product thoroughly before use.

AVAILABLE IN:

Metal tins of: 0.750 Litres; 4 Litres

STORAGE

24 months in closed original tin, under cover and at a temperature between 5 °C and 35 °C, and protected from the elements.

ADDITIONAL INFORMATION

The information contained in this document serves as a guide for the user but does not constitute a guarantee. For information about safety and the environment, please refer to the Safety Information File.
